



Specialty Dispersant

Smut Prevention Additive

1. Description

Specialty Dispersant is specifically formulated to prevent smut formation during the sealing process. It is applicable to either boiling water or high temperature nickel acetate sealing formulations.

2. Application instructions

Concentration: 3-6 g/l

3. Conditions for using Specialty Dispersant

Anodizing: To take advantage of the “smut-free” characteristic of this material, anodizing must be carried out under normal temperatures, 68-72°F.

Filtration: Field experience has shown that continuous filtration through a 5-35 micron filter is beneficial. **Do not use a carbon filter.**

4. Titration procedure

There is no analytical analysis for dispersant concentration control.

At the first sign of seal smut, and still passing seal tests, add 2-3 g/l of Dispersant to your sealant.

5. Packaging

50#

6. Storage

Store in original container in a cool dry location.

7. Product safety

We recommend that the company/operator read and review the **Material Safety Data Sheet** for the appropriate health and safety warnings before use.

U.S. Specialty Color Corporation® recommendations, notices or instructions as to handling, use, storage of any product, including its use alone or in combination with other products, or as to any apparatus or process for the use of any product, are based upon information believed to be reliable, but U.S. Specialty Color Corporation® shall have no liability with respect to any recommendations or instructions. U.S. Specialty Color Corporation® sole and exclusive warranty is that its products comply with U.S. Specialty Color Corporation® published chemical and physical specifications. U.S. Specialty Color Corporation® makes no other warranties, other express or implied with respect to its recommendations, instructions, products, apparatus, and process or otherwise and specifically disclaims any implied warranties of merchantability, suitability, fitness for a particular or otherwise.

11/1/11
Specialty Dispersant