



RO-59tm88 PTFE

1. Description

RO-59tm88 deposits a bonded PTFE coating on aluminum surfaces for high performance lubricity.

RO-59tm88 coatings will support a wide range of lubrication needs where performance properties of hardness, dry-film lubricity, release (non-sticking), endurance and corrosion protection is required.

- Unique bonding properties offer improved lubrication and longer wear ability.
- Meets AMS-2482, Type I
- Meets ASTM D1894-08
- Functional to 350°F
- Can be applied by immersion or spray.
- Environmentally safe to use.

2. Application instructions (See Section 5)

Concentration:	33% by volume
pH:	6.8-7.4
Temperature:	Ambient
Immersion time:	30 seconds - 2 minutes
Cure temperature:	175-200°F

3. Conditions for using RO-59tm88

Tank:	Tank must be of stainless steel, polypropylene or PVC.
Water quality:	Deionized
pH adjustments:	Raise with dilute ammonium hydroxide. Lower with dilute sulfuric acid. Rinse the probe thoroughly after each use, as it may become coated with PTFE.
Agitation:	Mix gently prior to use.
Cleaning:	A clean surface is necessary to ensure proper bonding and functionality of the PTFE coating. A clean metallic surface is indicated by a complete and uniform wetting of the surface by water with no dry spots, beading or streaking of water.
Cosmetics:	Cosmetically acceptable coatings are more likely to form by racking the work in a vertical position to allow drainage.
Dyed work:	Anodized work that has been dyed, should be sealed prior to immersion in PTFE.
Sealed work:	Parts must be allowed to cool to room temperature prior to immersion in PTFE.

4. Solution makeup

1. Fill tank 60% full of deionized water.
2. Slowly add the required amount of RO-59tm88 to the water.
3. Add deionized water very slowly to operating level and mix again.

5. Typical application cycle

1. Parts must be cool, completely clean and water-break free prior to immersion in RO-59tm88.
2. Dip the work in RO-59tm88 for 30 seconds - 2 minutes.
3. Remove the work and allow to air dry, then place in oven or hot room at 175-200°F for 30 minutes.

Multiple coating thickness:

A second coating to improve wear resistance is done by application + quick air dry (20-30 minutes) for the first coating, followed by reapplication + air dry (minutes) and placed in oven or hot room 175-200°F for 30 minutes.

6. Titration procedure

There is no Analytical procedure for concentration level.
Control by adding back 33% by volume of RO-59tm88 due to drag out.

7. Storage

Store in original container in a cool dry location.
Keep solution away from direct sunlight.
Maintain solution temperature above 50° and below 100°F.

8. Disclosure

All information is given under the express conditions that the party receiving it, will makes its own determination of its suitability.

9. Packaging

5 gallons
55 gallons

10. Product safety

We recommend that the company/operator read and review the **Safety Data Sheet** for the appropriate health and safety warnings before use.

U.S. Specialty Color Corporation® recommendations, notices or instructions as to handling, use, storage of any product, including its use alone or in combination with other products, or as to any apparatus or process for the use of any product, are based upon information believed to be reliable, but U.S. Specialty Color Corporation® shall have no liability with respect to any recommendations or instructions. U.S. Specialty Color Corporation® sole and exclusive warranty is that its products comply with U.S. Specialty Color Corporation® published chemical and physical specifications. U.S. Specialty Color Corporation® makes no other warranties, other express or implied with respect to its recommendations, instructions, products, apparatus, and process or otherwise and specifically disclaims any implied warranties of merchantability, suitability, fitness for a particular or otherwise.